

Lady Design Glaze

Product description

Type

This product is a high quality oil based glaze.

Features and benefits

Suitable for many different paint techniques such as sponging, ragging, colour wash and glazing. Comes in a beautiful selection of colours which will help you in creating the perfect look.

Recommended use

Specially formulated top coat for indoor use and recommended for Hotels, Restaurants, Villas and all other prestigious interiors.

Substrate

Cement plaster, Concrete, block work, gypsum board, rendered surfaces, MDF, plywood etc.

Substrate should have sufficient strength to receive the paint. Any defects in the substrate like surface undulations, cracks, pin holes etc., should be rectified/filled before starting painting.

Product data

Packaging size	0.5 L and 1 L Packing may vary from country to country according to local requirements.
Colours	Refer to the Lady Design Book.
Solids by volume	43 ± 2 volume% Theoretical
Specific gravity	0.93 Theoretical
VOC	475 g/l ISO 11890 EU
VOC comments	This is the theoretical value. Tested value will vary depending on test methodology, accuracy of equipment used for testing and test conditions.

Application data

The product can be applied by

Roller : Recommended.

Brush : Recommended.

Other tools may be used such as: Cotton, Rag, Sponge, Special Tools, 3M pad etc.

Film thickness per coat

Typical recommended range

Dry film thickness 25 - 40 µm

Film thickness will vary and is calculated as average.

Theoretical spreading rate 17.2 - 10.8 m²/l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Thinner

Jotun Thinner No. 2

Dilution

10-20%

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The moisture content in the substrate should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The drying time is measured by stated values:

Relative Humidity (RH) 50 %

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	24 h	12 h	6 h
Hard dry	96 h	48 h	24 h
Dry to over coat, minimum	96 h	48 h	24 h

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

Primer

Fenomastic Emulsion Primer : 1 Coat

Topcoat

Fenomastic Enamel Semigloss (10-20% Dilution) : 2 Coats

Lady Design Glaze : 1 - 2 Coats (As per desired finish.)

Other paint systems

On Wooden Surfaces:-

Bengalac Woodprimer : 1 Coat

Stucco : 2 Coats

Fenomastic Pure Colours Enamel Semigloss (10-20 Dilution %) : 2 Coats

Lady Design Glaze : 1 - 2 Coat(s) (As per desired finish.)

Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

This product is available in: United Arab Emirates, Bahrain, Kuwait, Qatar, Saudi, Oman, Egypt and Libya

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.